

6P 28206 (3)

EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER : 2000345299

PUBLICATION DATE : 12-12-00

APPLICATION DATE : 07-06-99

APPLICATION NUMBER : 11159347

APPLICANT : KOYO SEIKO CO LTD;

INVENTOR : TODA KAZUHISA;

INT.CL. : C22C 38/00 C23C 8/22 F16C 33/12 // C21D 1/06

TITLE : SLIDING PARTS

ABSTRACT : PROBLEM TO BE SOLVED: To improve wear resistance without deteriorating toughness and to prevent the occurrence of seizure.

SOLUTION: The sliding parts are obtained by applying heat treatment including carburizing treatment to a stock composed of steel. The content of C in the surface part is 0.9-3.0 wt.%, and surface hardness is ≥ 63 Rockwell C hardness. Fine spheroidal carbides are precipitated in the carburized layer, and the average grain size of the spheroidal carbides is $\leq 10 \mu\text{m}$ and the amount of the spheroidal carbides is $\leq 40\%$ by area ratio. Moreover, the grain size of $\geq 70\%$ of the spheroidal carbides is $\leq 10 \mu\text{m}$, and the amount of residual austenite in the carburized layer is 13-40%.

COPYRIGHT: (C)2000,JPO